

### TECHNICAL SHEET

#### DESCRIPTION

Wet look protective sealer, transparent and water-based for MicroConcrete surface. It is anti-dust. It prevents the crumbling of concrete. It is stain resistant, water repellent and easy to clean. Preserves the MicroConcrete color. Ideal for horizontal surfaces, such as countertops, floors or shower bases.



## WET LOOK

Water repellent



Low VOC



Waterborne products



**Available sizes**

1L and 3,64L



**Coverage**

**1L**

**1<sup>st</sup> coat:**

125 sq. ft to 150 sq. ft

**Additional coats:**

175 sq. ft to 250 sq. ft

**3,64L**

**1<sup>st</sup> coat:**

450 sq. ft to 550 sq. ft

**Additional coats:**

635 sq. ft to 910 sq. ft

## TECHNICAL SHEET

### APPLICATION

1. Stir the MicroConcrete sealer and let it rest for 5 to 10 minutes.
2. Pour in a paint tray.
3. Apply with a brush or roller or Finitec applicator, a thin coat making sure to saturate the surface with MicroConcrete.
4. Wait 2 hours before applying a second coat, make sure it is dry to the touch. See the application guide for detailed instructions.

ALL COATS MUST BE APPLIED WITHIN A MAXIMUM PERIOD OF 12 HOURS

### NUMBER OF COATS

Surfaces	Number of coats
Wall	1 to 2
Countertop, furniture, table, floor	2 to 3
Shower	4
Outside	2 to 4

### PHYSICAL PROPERTIES

Gloss	Wet look
Color	Translucid
VOC	166 g/L
pH	8,5 ± 0,1
Resistance to chemicals	Excellent
Drying time (depending on conditions)	Touch : between 1 and 2 hours Recoat : 2 hours Circulation: 12 hours
Density (g/mL)	1,03 ± 0,01

### TECHNICAL DATE

Coverage	<b>1L</b> 1 <sup>st</sup> coat : 125 sq. ft to 150 sq. ft Additional coats: 175 sq.ft to 250 sq.ft
	<b>3,64L</b> 1 <sup>st</sup> coat : 450 sq. ft to 550 sq. ft Additional coats: 635 sq. ft to 910 sq. ft
Available sizes	1L and 3,64L
Shelflife	12 months when kept in the original container)
Application tools	Finitec applicator, roller or brush
Cleaning tool	Water
Storage	Between 10 and 30 °C (50 and 85 °F)
Relative humidity	Between 45% and 80%
Application conditions	Between 10 and 30 °C (50 and 85 °F)

### FIRST AID

In case of eye or skin contact, rinse well with water for 15 minutes. In case of inhalation, allow the victim to rest in a well-ventilated area. If swallowed, seek medical attention. Do not induce vomiting. Have conscious person drink several glasses of water.

### WARNING

Exterior application: Apply the sealer at a temperature between 10°C and 30°C. Ensure there is no rain for the first 72 hours.